

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 62-154555

(43)Date of publication of application : 09.07.1987

1)Int.Cl.

H01M 2/08

1)Application number : 60-292922

(71)Applicant : NIPPON PETROCHEM CO LTD

2)Date of filing : 27.12.1985


(72)Inventor : YANAGI TOSHIO
GOSHI YOSHIHIRO

4) BATTERY

7)Abstract:

PURPOSE: To provide a battery having good electrolyte leakage resistance by using a sealant comprising isobutylene family polymer containing wax.

CONSTITUTION: A gap 5 in a battery sealing part is sealed with a sealant 4 made of a polymer mainly comprising isobutylene having a mean molecular weight of 700~10,000 containing 1~30wt.% wax. As the wax, animal and plant wax and preferably hydrocarbon wax such as paraffin wax, microcrystalline wax, polyethylene wax, and atactic polypropylene (APP) wax is used. Isobutylene polymer having mean molecular weight less than 700 has low viscosity and its sealing ability is insufficient. isobutylene polymer having mean molecular weight exceeding 10,000 has too high viscosity and it makes coating difficult.



GAL STATUS

Date of request for examination]

Date of sending the examiner's decision of rejection]

Kind of final disposal of application other than the
examiner's decision of rejection or application
converted registration]

Date of final disposal for application]

Patent number]

Date of registration]

Number of appeal against examiner's decision of
ejection]

Date of requesting appeal against examiner's
ecision of rejection]

Date of extinction of right]

Copyright (C); 1998,2000 Japan Patent Office